

LFT

Direct Roving for
Long Fiber Thermoplastic
Applications



PRODUCT FEATURES

- Boron-free ECR-glass
- Environment friendly
- Good unwinding
- Low fuzz
- Good & fast wettability
- Excellent tex distribution
- High mechanical performance

PRODUCT SPECIFICATION

LFT

• Glass Type	ECR (B-Free)
• Filament Diameter (μ)	Nom. 17
• Roving Tex ($\text{g}/10^3\text{m}$)	1200-2400 $\pm$ % 7
• Moisture Content (%)	Max. 0,1
• Sizing Type	Silane
• Loss of Ignition (%)	0,7 $\pm$ 0,15
• Compatability	Polypropylene, Polyethylene

PACKAGING

Type	Pallet Dimensions (cm)	Bobbins per Pallet	Layers per Pallet	Pallet Height (cm)	Product Net Weight per Pallet (kg)
Bulk Packaging	96 x 128	48	4	120 +/- 10	864

BOBBIN DIMENSIONS


Weight (kg)	Inner diameter(mm)	Outer diameter(mm)	Height(mm)
Nom. 18	160	295	255

STORAGE

Products should be stored in original package in dry and dust free area.
Storage temperature is between 10°C - 30°C at humidity between 50% - 75%.

WARRANTY

All physical & chemical properties represent average values and subject to normal production variations.
The specifications are also subject to change. For current information please contact Beşler Office.



BESLER
GLASS FIBER