

PR

Assembled Roving for
Panel Applications



PRODUCT FEATURES

- Boron-free ECR-Glass
- Environment friendly
- Good unwinding
- Good wet out
- Good choppability
- Low fuzz & static

PRODUCT SPECIFICATION

PR

• Glass Type	ECR (B-Free)
• Filament Diameter (μ)	Nom. 13
• Roving Tex (g/10 ³ m)	2400 ± % 5
• Split Tex (g/10 ³ m)	Nom. 33
• Moisture Content (%)	Max. 0,1
• Sizing Type	Silane
• Loss of Ignition (%)	0,85 ± 0,15
• Compatability	Polyester, Epoxy

PACKAGING

Type	Pallet Dimensions (cm)	Bobbins per Pallet	Layers per Pallet	Pallet Height (cm)	Product Net Weight per Pallet (kg)
Cardboard	93 x 123	48	4	120 +/-5	1032

BOBBIN DIMENSIONS


Weight (kg)	Inner Diameter(mm)	Outer Diameter(mm)	Height(mm)
Nom. 21,5	75	295	255

STORAGE

Products should be stored in original package in dry and dust free area.
Storage temperature is between 10°C - 30°C at humidity between 50% - 75%.

WARRANTY

All physical & chemical properties represent average values and subject to normal production variations.
The specifications are also subject to change. For current information please contact Beşler Office.



BESLER
GLASS FIBER